Flowfresh RT (6 to 9mm)

A slip-resistant HACCP International Certified antimicrobial treated polyurethane screed.



Heat Resistant:

Resistant to temperatures of up to 120°C



Slip Resistant:

Impressive anti-slip profile in dry and wet conditions.



Hygienic:

Contains Polygiene® - an antimicrobial additive that kills up to 99.9% bacteria.



Chemical Resistant:

Protects against the majority of acids used in manufacturing processes.



Durable:

Holds its own against impact as well as heavy traffic.



The applied colours may differ from the examples shown.


For a full colour chart and samples, contact your regional Flowcrete office.

Technical Profile

FIRE RESISTANCE		
BS 476-7	Class 2	
WATER PERMEABILITY		
Karsten Test	Nil (Impermeable)	
TEMPERATURE RESISTANCE		
-25°C to 100°C at 6mm, -45°C to 120°C at 9mm		
SLIP RESISTANCE		
TRRL Pendulum Slip Test	Dry: >80	
	Wet: >35	
COMPRESSIVE STRENGTH		
BS 6319	>60 N/mm²	
FLEXURAL STRENGTH		
BS 6319	>20 N/mm²	
TENSILE STRENGTH		
BS 6319	>10 N/mm²	
BOND STRENGTH		
>1.5 MPa concrete failure		
COEFFICIENT OF THERMAL EXPANSION		
ASTM C531	3.74 x 10 ⁻⁵ °C ⁻¹	
VOC EMMISSIONS		
USEPA Method 24	56.27g/L	
* The confirmation and a section of the confirmation of the confir	ation in although the balls are as a constraint	

20°C and at 50% Relative Humidity.	

SPEED OF CURE	10°C	20°C	30°C
Light Traffic	36 hrs	24 hrs	12 hrs
Full Traffic	72 hrs	48 hrs	24 hrs
Full Chemical Cure	10 days	7 days	6 days



November 2021 (Flowfresh RT)

For applications falling outside of this temperature range, please contact your local Flowcrete Technical Department

Model Specification

	System	Flowfresh RT	
	Finish	Textured	
	Thickness	6 to 9mm	

Preparatory work and application in accordance with manufacturer's instructions.

Products Included in this System

Primer	Flowprime / Flowfresh Primer	
Scatter	Scatter 3	
Screed	Flowfresh RT	

Substrate Requirements

Concrete or screed substrate should be a minimum of 25N/mm², and maintain a minimum tensile strength of 1.5 MPa, free from laitance, dust and other contamination. The substrate should have a moisture content of no more than 5%.

Installation Service

The installation should be carried out by an Approved Applicator. For details on our Approved Applicators, contact our regional office. Detailed application instructions are available upon request.

Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent

Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs and maintenance. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained application teams.

Focus on the Floorzone

Flowcrete is a market leader in specialist industrial and commercial flooring. Systems available include: floor screeds, surface damp proof membranes, decorative flooring, seamless terrazzo, car park deck coatings, tank lining systems ... to name just a few. Our objective is to satisfy your Floorzone needs.

Polygiene® and HACCP International

Flowfresh flooring systems are antimicrobial to ISO 22196 standard, owing to the inclusion of Polygiene®, an antimicrobial additive incorporated in the formulation. The Flowfresh range of floor systems is HACCP International certified as safe for use in food environments.

Warranty

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard "Warranty, Terms and Conditions of Sale", copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.

November 2021 (Flowfresh RT)